

SAN FEDELINO

<i>Physical-Mechanical Characteristics</i>	<i>Average Values</i>
Apparent Density	2,630 Kg/mc
Imbibition Coefficient	2.38%
Indirect tensile strength by flexural strength	17.3 MPa
Abrasion Coefficient on the Tribometer	1
Petrographic Definition	Granite